









Product properties	
Format	2200 x 185 x 11.5 mm
Top layer	≥ 2.5 mm
Packaging	10 Elements
Pack	4.07 m ² / 29.30 Kg
Pallet	32 Packs 130.24 m ² / 937.60 Kg
Warranty	10 years
Notes	- cleaning an maintenance see intruction - technical changes reserved

Product labeling	
       	Only laquered products:

Tolerances (EN 13489)	
Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.1 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.1 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 – 8 %

Classification Specifications			
		Testing standard	Valuation
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
	Effect of a furniture leg	EN 424	No visible changes
	Thermal conductivity Underfloor heating – suitable, with the backing material an vapor barrier	EN 12664	0.077 m ² *K/W
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0.05 ppm
	Accoustical impact noise reduction	ISO 717-2	14 db (with Akustic-Protect 100)
	Disposal		Privat waste disposal with normal haushold waste, bulky waste possible

Classification surface properties				
		Testing standard	Valuation	
			Lacquer	Naturoil
	Slip resistance	EN 13893	μ ≥ 0.47	μ ≥ 0.47
		CEN/TS 15676	29 SRT (SRV wet)	46 SRT (SRV wet)
			51 SRT (SRV dry)	103 SRT (SRV dry)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D _{fl} s1	
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D _{fl} s1	
	Chemical resistance	EN 13442	Category 5	Category 4
	Bond strength / Gross cut test	ISO 2409	0	n.n.
	Slip resistance, inclined plane	DIN 51130	R 9	R 10

Changed:	QMB	File name:	PA_TDS_Parkett_Basic_EN_08102015
Date:	01.08.2013	Update:	www.parador.de
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			
			08.10.2015

Free sorting according to EN 13489								
Assortment:	Block						Wide plank	
Characteristics according to EN 1310:	Upper side of the lamella						Upper side of the floor board	
Type of wood:	Canadian maple	Mountain maple, european	Beech	Oak	European cherry	American walnut	Oak	
Botanical designation / Code (EN 13556):	Acer saccharum Marsh. / ACSC	Acer pseudoplatanus L. / ACPS	Fagus sylvatica L. / FASY	Quercus petraea Liebl., Quercus robur L. / QCXE	Prunus avium L. / PRAV	Juglans nigra L. / JGNG	Quercus petraea Liebl., Quercus robur L. / QCXE	
Origin:	CA	BA, HR	HU, HR, SK, BA	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ	BA, HR	US	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ	
Shortcut / sorting / date (internal):	ER-L-AHC	ER-L-BAH	ER-L-BU	ER-L-EI	ES-L-KIR	ER-L-SWN	ER-LH-EI	
	Version 6 2012	Version 6 2012	Version 6 2012	Version 7 2012	Version 4 2012	Version 6 2012	Version 5 2013	Version 2 2012
	A2	A4	A2	A4	A4	A4	N3	N7
Sorting:	Natur	Rustikal	Natur	Rustikal	Rustikal	Rustikal	Classic	Rustikal
Sound sapwood	-	-	-	permitted	permitted	permitted	not permitted	permitted
Knot (intergrown)	permitted: up to 15 mm	permitted: up to 30 mm	permitted: up to 15 mm	permitted: up to 20 mm	permitted: up to 30 mm	permitted: up to 30 mm	permitted: up to 30 mm	permitted: up to 80 mm
Falling out knot	not permitted	not permitted	not permitted	permitted: up to 20 mm	not permitted	not permitted	permitted: up to 15 mm	permitted: up to 30 mm
Pinkknots	permitted	permitted	permitted	permitted	permitted	permitted	permitted: cluster of knots	permitted: cluster of knots
Filling	permitted: up to 10 mm	permitted: up to 20 mm	permitted: up to 10 mm	permitted: up to 20 mm	permitted: up to 20 mm	permitted: up to 20 mm	permitted	permitted
Slight crack/ haircrack	not permitted	not permitted	not permitted	not permitted	not permitted	permitted	not permitted	permitted
Sugar inclusions, mineral inclusions	permitted: max. 150 x 3 mm	-	-	-	-	-	-	-
Bark pocket	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	-
Lightning cracks	not permitted	permitted	permitted	permitted	-	permitted	permitted	permitted
Slope of grain	all features permitted	all features permitted	all features permitted	all features permitted	all features permitted	all features permitted	permitted	permitted
Healthy heart	permitted	permitted	permitted	-	-	-	permitted	permitted
Medullary ray	permitted	permitted	permitted	permitted	permitted	-	permitted	permitted
Discoloration, colour variation	permitted	permitted	permitted	permitted	permitted	permitted	permitted	permitted
White streaks	-	-	-	permitted	-	-	-	permitted
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts								
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.								
Comment								
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.								

Changed:	QMB	File name:	PA_TDS_Parkett_Basic_Anhang_EN_08102015
Date:	01.08.2013	Update:	www.parador.de
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			08.10.2015
			Page 1 of 1