









Product properties	
<b>Format</b>	1593 x 215 x 15 mm
Top layer	≥ 3.6 mm
<b>Packaging</b>	8 Elements
Pack	2.74 m <sup>2</sup> / 25.98 Kg
Pallet	32 Packs 87.679 m <sup>2</sup> / 831.36 Kg
<b>Warranty</b>	25 years
Notes	- cleaning an maintenance see intruction - technical changes reserved

Product labeling			
 EN 14342 : 08			

Tolerances (EN 13489)	
Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.1 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.1 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 – 8 %

Classification Specifications			
		Prüfnorm	Bewertung
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
	Effect of a furniture leg	EN 424	No visible changes
	<b>Thermal conductivity</b> Underfloor heating – suitable, with the backing material an vapor barrier	EN 12664	0.1 m <sup>2</sup> *K/W
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0.05 ppm
	Accoustical impact noise reduction	ISO 717-2	12 db (with Akustic-Protect 100)
	Disposal		Privat waste disposal with normal haushold waste, bulky waste possible

Classification surface properties			
		Testing standard	Valuation
	Slip resistance	EN 13893	μ ≥ 0.47
		CEN/TS 15676	46 SRT (SRV wet)
			103 SRT (SRV dry)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D <sub>fl</sub> s1
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D <sub>fl</sub> s1
	Chemical resistance	EN 13442	Category 4
	Bond strength / Gross cut test	ISO 2409	n.n.
	Slip reststance, inclined plane	DIN 51130	R 10

Changed:	QMB	File name:	PA_TDS_Parkett_Edition_EN_2015
Date:	01.08.2013	Update:	<a href="http://www.parador.de">www.parador.de</a>
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.01.2015

Free sorting according to EN 13489	
<b>Assortment:</b>	<b>Herringbone pattern</b>
Characteristics according to EN 1310:	Upper side of the lamella
<b>Type of wood:</b>	<b>Oak</b>
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE
Origin:	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ
Shortcut / sorting / date (internal):	ER-L-FGF-EI
	Version 1
	2013
	N2
<b>Sorting:</b>	<b>Select</b>
Sound sapwood	not permitted
Knot (intergrown)	not permitted
Falling out knot	not permitted
Pinkknots	permitted: up to 5 mm
Filling	permitted: up to 5 mm
Slight crack/ haircrack	not permitted
Sugar inclusions, mineral inclusions	-
Bark pocket	not permitted
Lightning cracks	not permitted
Slope of grain	permitted: straight flader
Healthy heart	-
Medullary ray	permitted
Discoloration, colour variation	permitted: slight color variation
White streaks	-
Pilling sticks marking	not permitted
Biodegradation (EN 1311)	not permitted
<b>Non-visible parts</b>	
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.	
<b>Comment</b>	
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.	

Changed:	QMB	File name:	PA_TDS_Parkett_Edition_Anhang_EN_2015
Date:	01.08.2013	Update:	<a href="http://www.parador.de">www.parador.de</a>
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:		01.01.2015	Page 1 of 1