























Product quality		Trendtime 5.50	Trendtime 5.30	Trendtime 6.30	
		Vinyl with HDF core board			
<b>Formats</b>		598 x 294 x 5 mm	598 x 292 x 9.6 mm	2200 x 216 x 9.6 mm	
<b>Packaging</b>	<b>Pack:</b>	10 Elements / 1.758 m <sup>2</sup> / 16.20 Kg	9 Elements / 1.572 m <sup>2</sup> / 15.40 Kg	5 Elements / 2.376 m <sup>2</sup> / 23.50 Kg	
	<b>Pallet:</b>	48 Packs / 84.39 m <sup>2</sup> / 792.60 Kg	36 Packs / 56.58 m <sup>2</sup> / 569.364 Kg	33 Packs / 78.41 m <sup>2</sup> / 790.50 Kg	
<b>Tolerances (DIN EN ISO 10582)</b>			<b>Tolerances (EN 14085)</b>		
<b>Weight per unit area</b>		≥ 9700 g/m <sup>2</sup>	<b>Squareness of the elements (≤ 0.50mm)</b>		
<b>Squareness of the elements (≤ 0.25 mm)</b>		≤ 0.10 mm	<b>Determination of Linearity (≤ 0.30 mm)</b>		
<b>Determination of Linearity (≤ 0.35 mm/m)</b>		≤ 0.20 mm/m	<b>Planeness</b> concave / convex		
			<b>along (≤ 0.50/≤ 1.0 %)</b>		
			<b>wide (≤ 0.10/≤ 0.15 %)</b>		
			<b>Surface flushness</b>		
			<b>(average ≤ 0.15 mm)</b>		
			<b>(max. ≤ 0.20 mm)</b>		
			<b>Opening between installet elements</b>		
			<b>(average ≤ 0.15 mm)</b>		
			<b>(max. ≤ 0.20 mm)</b>		
<b>Guarantee</b>	Domestic area	20 Years (According Parador guarantee conditions)	<b>Notes</b>	<ul style="list-style-type: none"> <li>- Released for glue-down only by PARADOR Application Technology</li> <li>- cleaning an maintenance see instruction</li> <li>- technical changes reserved</li> </ul>	
	Commercial area	10 Years (According Parador guarantee conditions)			
 EN 14041:08			 Qualität Fertigung überwacht Funktionalität www.tuv.com ID 0000039917		

Classification			
		Test method	Valuation
	<b>Utility class 23</b> domestic areas with intensive use	EN 14085 DIN EN ISO 10582	Living room, hall, kitchen, home office
	<b>Utility class 33</b> commercial areas with intensive use	EN 14085 DIN EN ISO 10582	Classrooms, small offices, shops
	<b>Utility class 42</b> industrial areas with medium use	EN 14085 DIN EN ISO 10582	Storage rooms or moderately used Production areas
	Wearlayer	EN 429	0.55 mm
	Abrasion	DIN EN ISO 10582	T
	Surface Coating		PUR
	Reaction to fire	EN 13501-1	B <sub>fl</sub> s1
	Slip resistance	EN 13893 EN 14041	μ ≥ 0,35 DS
	Staining resistance	EN 423	Grad 0, no visible changes
	Light fastness	EN ISO 105 - B02	Blue wool scale: Stage ≥ 6
	Resistance to roller castor chairs	EN 425	Typ W, no visible changes
	<b>Thermal conductivity</b> Underfloor heating – suitable, with the backing material and vapor barrier	EN 12664	Vinyl with HDF core board: 0,068 m <sup>2</sup> *K/W Solid vinyl: 0,029 m <sup>2</sup> *K/W
	Moving a furniture leg	EN 424	No visible changes
	Indentation-residual	EN 433	≤ 0,10 mm
	Formaldehyde (E1 = 0.1 ppm)		≤ 0,05 ppm
	Accoustical impact noise reduction	ISO 717-2	Vinyl with HDF core board: 15 db Solid vinyl: 13 db (auf Parador Akustic-Protect)
	Dimensional stability	EN 669	Vinyl with HDF core board: along and crosswise ≤0,1 % Solid vinyl: ≤ 0,25 %
	Thickness swelling	ISO 24336 (≤ 18 %)	≤ 16 % (only Solid vinyl:)
	Antimicrobial activity	ISO 22196	Antibacterial
	Slip resistance on an inclined plane	DIN 51130	Surface brushed: R 9 Surface rough sawn: R 10
	REACH		Current requirements are complied
	Disposal		Privat waste disposal with normal haushold waste, bulky waste possible

Changed:	QMB Parador	File:	PA_TDS_Vinyl_Trendtime_EN_10092015
Date:	01.06.2012	Updates at:	<a href="http://www.parador.de">www.parador.de</a>
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			10.09.2015